

Need Metal? We get it!

SpecMet CSF-316L(P)

AWS A5.22 E316LT1-1/4
KS D 3612 YF316LC
JIS Z 3323 TS316L-FB1
EN ISO 17633-A T 19 12 3 L P C1[M21] 1 - IIO 17633-B TS 316L-F C1[M21] 1

Applications

CSF-316L(P) is suitable for welding of low carbon 18%Cr-12%Ni-2%Mo stainless steel.

Characteristics

- (1) CSF-316L(P) is flux cored wire and designed for Fillet & H-F(All-position) welding with CO₂ gas Shielding.
- (2) It provides the excellent usability with stable arc, less spattering, good bead appearance, better slag removal, and less quantity of welding fume comparable to solid wire.
- (3) Is containing Ferrite of a reasonable quantity and crack-resistance, intergranular corrosion resistance, mechanical properties of weld metal is superior.
- (4) Shield gas is 100% CO₂ or Ar+CO₂ gas.

Notes on Usage

- (1) The optimum flow of CO₂ for Shielding is 20~25l/min.
- (2) Protect the weld with a screen to prevent blowholes caused by wind where the wind velocity is 2m/sec and more.
- (3) Keep the distance between tip & base metal at 15~25mm.

Typical Chemical Composition of Weld Metal (%) (shielding gas: 100% CO₂)

	C	Mn	Si	P	S	Cr	Ni	Mo	FN
316L	0.03	1.45	0.60	0.019	0.012	18.5	12.4	2.20	8
316LP	0.03	1.20	0.60	0.020	0.008	18.6	12.5	2.50	7
^{316LP} CRYOGENIC	0.03	1.25	0.50	0.020	0.008	18.4	12.8	2.30	6

Typical Mechanical Properties of Weld Metal (%) (shielding gas: 100% CO₂)

	YS N/mm ² (MPa)	TS N/mm ² (MPa)	EL (%)	IV (J) 0° C	IV (J) -196° C
316L	425	565	43	55	-
316LP	420	560	45	54	-
^{316LP} CRYOGENIC	425	560	44	57	35

Size and Recommended Current Range (AC or DC+)

Dia mm (in)	Current (A)	Volatage (V)	Welding Speed (cm/min)
1.2 (0.045)	150~300	24~33	20~60
1.6 (0.062)	200~400	24~33	20~60

Approval : CSF-316L : ABS, BV, DNV, GL, KR, LR, NK / CSF-316LP(for cryogenic) : ABS, BV, DNV, LR