

Need Metal? We get it!

SpecMet CSF-71U

AWS A5.20 E71T-9C - A5.36 E71T1-C1A2-CS1
KS D 7104 YFL-C503R
JIS Z 3313 T493T1-1CA-N1-H10
EN ISO 17632-A T46 3 P C 1 - ISO 17632-B T49 3 T1-1 C A-N1

Applications

Butt, fillet welding of 490N/mm² class high strength steel and low temperature steel of structure such as ships, bridges, buildings and storage tanks etc

Characteristics

- (1) CSF-71U is a titania type flux cored wire and designed for all-position welding by single pass & multi pass with CO₂ gas shielding.
- (2) It provides the excellent usability with stable arc, less spattering, good bead appearance, better slag removal, and less quantity of welding fume comparable to solid wire.
- (3) It provides a good welding efficiency thank to high deposition rate particularly.
- (4) Weld metal has good impact properties at -30°C.

Notes on Usage

- (1) The optimum flow of CO₂ for shielding is 20~25l/min.
- (2) The distance between tip & base metal is to be 20~25mm.
- (3) Protect the weld with a screen to prevent blowholes caused by wind where the wind velocity is 2m/sec and more.
- (4) Thick heavy plate should be welded under proper preheating & interpass temperature.

Typical chemical composition of weld metal (%) (shielding gas: 100% CO₂)

C	Mn	Si	P	S
0.04	1.41	0.36	0.013	0.010

Typical mechanical properties of weld metal (%) (shielding gas: 100% CO₂)

YP N/mm ² (MPa)	TS N/mm ² (MPa)	EL (%)	IV (J)	
			-20°C	-30°C
504	584	28.0	130	95

Size and recommended current range (DC+)

Dia. Mm(in)		1.2 (0.045)	1.4 (0.052)	1.6 (0.062)
Flat H-Fillet	Amp	180~340	200~360	200~400
V-Up	Amp	120~220	140~260	160~260
V-Down	Amp	120~240	140~260	160~280
O.H	Amp	120~220	140~260	160~260

Approvals: ABS, BV, DNV, GL, LR, NK